



COEFFICIENTS OF FRICTION - EW Gold (Sandblasted)

Lab No. 50P-0156

SAMPLE ID: EW Gold Slip Resistant 3/13/10

TEST EQUIPMENT / TYPE: Dynamometer-INSTRON Tester, Model #1011

TEST METHOD: Testing performed in accordance with ASTM C 1028-06

CONDITIONING: 72° F / 50% RH for 24 Hours

TEST CONDITIONS: Wet/Dry

TEST PLANE: Neolite Heel Assembly w/50 lbs. of weight

STATIC COEFFICIENT OF FRICTION (WET): .614

STATIC COEFFICIENT OF FRICTION (DRY): .734