



4287 N. Hwy 51 - Perryville, MO 63775
800.887.4555 - Fax 573.547.6067

16900-A Baxter Rd - Chesterfield, MO 63005
800.532.9510 - Fax 636.537.2786

www.EarthworksStone.net
info@EarthworksStone.net

Earthworks Stone Testing Data

DOVE GRAY

Report No. A-430068

Test Conducted

Unconfined	
Compressive Strength	14,320 psi
Bulk Specific Gravity	2.58
Weight per Cubic Ft	160.99 lb
Bulk Specific Gravity, SSD	2.62
Apparent Specific Gravity	2.69
Absorption, %	1.60

Note 1: Unconfined compressive strength was conducted in accordance with ASTM Specification D2938.

Note 2: Absorption was conducted in accordance with ASTM D2216.

Note 3: Specific gravity was conducted in accordance with ASTM C127.