



4287 N. Hwy 51 - Perryville, MO 63775  
800.887.4555 - Fax 573.547.6067

16900-A Baxter Rd - Chesterfield, MO 63005  
800.532.9510 - Fax 636.537.2786

www.EarthworksStone.net  
info@EarthworksStone.net

## Earthworks Stone Testing Data

### **PEWTER MIST**

All tests results were provided by SGS U.S. Testing Company Inc., Tulsa, Oklahoma.

#### **ASTM C 97**

Absorption 2.91%  
Dimensional Density 149.24 lb/ft<sup>3</sup>  
Dimensional Specific Gravity 2.39

#### **ASTM C 99**

Modulus of Rupture, psi 1922

#### **ASTM C 170**

Compressive Strength, psi 10720

#### **ASTM C 241**

Abrasion Index 12.59  
Bulk Specific Gravity 2.439

#### **ASTM C 880**

Flexural Strength, psi 1578